











GRES PORCELLANATO IMPASTO COLORATO

Colored Body Porcelain Stoneware / Grès Cérame Masse Coloré / Feinsteinzeug mit Eingefärbten Scherben

UNI EN 14411 Bla Allegato G (ISO 13006)

Caratteristica tecnica Technical feature Caractéristique technique Technische Eigenschaft	Norma Norm Norme Norm	Valore richiesto dalle norme Required standards Valeur prescrite par les normes Normvorgabe	ERMETICA		
 Lunghezza e larghezza / Length and width Longuer et largeur / Länge und breite  Spessore / Thickness / Epaisseur / Stärke Rectilinéarité spigoli / Straightness of sides Rectitude des arêtes / Kantengeradheit Ortogonalità / Rectangularity Orthogonalité / Rechtwinkligkeit Planarità / Length and width Planeité de surface / Ebenflächigkeit	UNI EN ISO 10545-2	N ≥ 15 cm % ± 0,6 Non Rect. ± 0,3 Rect. ± 5 ± 0,5 Non Rect. ± 0,3 Rect. ± 0,5 Non Rect. ± 0,3 Rect. ± 0,5 Non Rect. ± 0,4 Rect.	(mm) ± 2,0 Non Rect. ± 1,0 Rect. ± 0,5 ± 1,5 Non Rect. ± 0,8 Rect. ± 2,0 Non Rect. ± 1,5 Rect. ± 2,0 Non Rect. ± 1,8 Rect.	Conforme Corresponding Conforme Entsprechend	
		Qualità della superficie Surface quality Qualités de la surface Oberflächenqualität	UNI EN ISO 10545-2	Il 95 % min. delle piastrelle di prova deve essere esente da difetti visibili Minimum 95% of the tested tiles must be free from visible defects 95% min. des carreaux de test ne doit pas contenir de défauts visibles Min. 95% der geprüften Fliesen dürfen keine sichtbaren Mängel aufweisen	Conforme Corresponding Conforme Entsprechend
		Assorbimento d'acqua / Water absorption Absorption d'eau / Wasseraufnahme	UNI EN ISO 10545-3	≤ 0,5% Individual max 0,6%	≤ 0,5%
		Sforzo di Rottura / Breaking strength Effort de rupture / Bruchkraft  Resistenza alla flessione / Modulus of Rupture Résistance à la flexion / Biegefestigkeit	UNI EN ISO 10545-4	S ≥ 1300 N (≥ 7,5 mm) R ≥ 35 N/mm ²	S ≥ 1300 N R ≥ 35 N/mm ²
 Resistenza all'abrasione (metodo PEI) Abrasion resistance (PEI test) Résistance à l'abrasion (méthode PEI) Widerstand gegen Abrieb (nach PEI)	UNI EN ISO 10545-7	Segnala la classe di abrasione e i cicli superati Report abrasion class and cycles passed	LAVAGNA PEI IV BIANCO - CREMA - GRIGIO PEI V		
 Resistenza al gelo / Resistance to frost Résistance aux gel / Frostbeständigkeit	UNI EN ISO 10545-12	Richiesto Required	Non gelivo / Frost-proof Non gélifs / Frostsicher		
 Resistenza ai prodotti chimici Resistance to chemical products Résistance aux produits chimiques Widerstand gegen Chemikalien	UNI EN ISO 10545-13	Resistenza a basse concentrazioni di acidi e alcali Resistance to low concentrations of acids and alkalis Secondo la classificazione indicata dal fabbricante Manufacturer is to state classification	LA		
		Resistenza ad alte concentrazioni di acidi e alcali Resistance to high concentrations of acids and alkalis Metodo di prova disponibile Test method available	HA		
		Resistenza ai prodotti chimici di uso domestico ed agli additivi per piscina Resistance to household chemicals and swimming pool salt Classe minima B Minimum class B	A		
 Resistenza alle macchie Staining resistance Résistance aux taches Widerstand gegen Fleckenbildung	UNI EN ISO 10545-14	Min. 3	Conforme Corresponding Conforme Entsprechend		
 Resistenza agli sbalzi termici Thermal shock resistance Résistance aux écarts de température Temperaturwechselbeständigkeit	UNI EN ISO 10545-9	Metodo di prova disponibile Test method available	Resiste Resistant Résiste Widerstandsfähig		
Caratteristiche accessorie / Additional features					
 Stabilità dei colori / Colours stability Stabilité des couleurs / Farbbeständigkeit	DIN 51094	Colorazione Stabile Stable coloring	Conforme / Corresponding Conforme / Entsprechend		
Caratteristiche di sicurezza / Safety characteristics					
 Resistenza allo scivolamento Slip resistance Résistance au glissement Rutschemmende Eigenschaft	METODO B.C.R.A.	μ > 0,40	Conforme / Corresponding Conforme / Entsprechend		
	DIN EN 16165	ANNEX A Test della rampa a piedi nudi / Classe dichiarata Barefoot ramp test / Declared Class Méthode de la rampe pieds nus / Classe déclarée Methode der schiefen Ebene, barfuß / Angegebene Klasse	A+B		
		ANNEX B Test della rampa a piedi calzati / Classe dichiarata Shod ramp test / Declared Class Rampe avec chaussures / Classe déclarée Methode der schiefen Ebene, mit Schuhwerk / Angegebene Klasse	R10		
	DCOF (ANSI A 326.3)	≥ 0,42	Conforme / Corresponding Conforme / Entsprechend		